

SSWP 400 is a heat-treated smooth surface wear plate for high abrasion resistance applications in mining, steel, cement and construction industries. Can be easily welded, cut and formed for accurate fabrication. Through- hardness of the plate provides longer service life.

Unique Features:

- Excellent resistance to sliding abrasion
- Excellent resistance to impact
- Through-hardened
- Good weldability and fabrication
- Excellent response to Oxy, Plasma and Laser cutting and machining.
- Superior flatness
- Smooth surface finish

Typical Properties:

Hardness: 400 BHN

Microstructure: Tempered Martensitic structure found throughout the section.

Welding:

EWAC SSWP 400 exhibits excellent weldability. It is recommended that the plate should be preheated and no post heating is required. Avoid exposure to high service temperature in excess of 250 °C.

Fabrication:

EWAC can supply the fabricated sections as per drawings / requirements.

Applications:

SSWP 400 is suited for applications involving high impact and moderate abrasion. Applications include Chute Liners, Truck Beds, Dipper Liners, Shovels, Bucket Liners, Scrapers, Screens, Crusher Parts, Conveyors, Hoppers, Chute liners, Bin and hopper liners, Construction and mining bucket liners, Mold board liners, Scrapper liners.

Other Grades:

SSWP 500 grade is also available with hardness 500 BHN.

EWAC Alloys Limited

Marketing & Head Office:

L&T Business Park, Tower - B, TC - II, 5th Floor, L&T Gate No. 5, Powai Campus, Saki Vihar Road, Powai, Mumbai - 400 072, INDIA.

Tel: 022 6705 9830 / 7 / 8, Fax: 022 6705 9876, Email: enquiry@ewacalloys.com, Web: www.ewacalloys.com, CIN: U74999MH1962PLC012315

Zonal Office: Vadodara: 0265 6613 607 / 8, Chennai: 044 4070 6896, Chhattisgarh: 0771 4283 206 / 9, Hyderabad: 040 2323 0689, Delhi: 011 4141 9538 / 40, Kolkata: 033 2282 0227, Pune: 020 6603 3211